

Please amend the claims as follows:

1. (Currently Amended) A solid pigment preparation comprising
 - (A) at least one pigment in a higher concentration than that which corresponds to the subsequent application and
 - (B) at least one carrier material selected from the group consisting of oligomers and polymers which have a glass transition temperature $> 30^{\circ}\text{C}$ and a melting point or melting range below their decomposition temperature,

~~preparable~~ prepared by dispersing the pigment or pigments (A) or the pigment or pigments (A) and at least one constituent (D) in the melt of the carrier material or carrier materials (B) or in the melt of the carrier material or carrier materials (B) and at least one constituent (D) ~~with a power input of from 0.1 to 1.0 kW/kg for from 0.5 to 5 hours in a discontinuously operating dispersing apparatus~~ with a power input of from 0.1 to 1.0 kW/kg, and then discharging the mixture (A/B) or (A/B/D) from the dispersing apparatus and allowing it to cool and solidify.
2. (Original) The pigment preparation as claimed in claim 1, which is in powder form.
3. (Original) The pigment preparation as claimed in claim 1, which is in the form of a dispersion in at least one organic solvent (C).
4. (Currently Amended) The pigment preparation ~~as claimed in any of claims 1 to 3~~ of claim 1, wherein the pigments (A) are selected from the group consisting of organic, ~~and~~ inorganic, transparent, ~~and~~ opaque, color, ~~and/or~~ effect, fluorescent, phosphorescent, electrically conductive, and magnetically shielding pigments, ~~and transparent metal powders, and opaque metal powders, and also organic fillers and nanoparticles, and inorganic fillers and nanoparticles,~~ transparent and opaque fillers and nanoparticles.
5. (Currently Amended) The pigment preparation ~~as claimed in any of claims 1 to 4~~ of claim 1, wherein the oligomers and polymers (B) have a glass transition temperature of between 30 and 200°C .

6. (Currently Amended) The pigment preparation ~~as claimed in any of~~
~~claims 1 to 5 of claim 1~~, wherein the oligomers and polymers (B) do not
decompose within a temperature range of at least 100°C above their glass
transition temperature.
7. (Currently Amended) The pigment preparation ~~as claimed in any of~~
~~claims 1, 2 or 4 to 6, of claim 1, containing or comprising~~, based on the
pigment preparation, from 1 to 85% by weight of at least one pigment (A)
and from 15 to 99% by weight of at least one carrier material (B).
8. (Currently Amended) The pigment preparation ~~as claimed in any of~~
~~claims 3 to 6 of claim 3~~, comprising, based on the solids of the dispersion,
from 1 to 85% by weight of at least one pigment (A) and from 15 to 99%
by weight of at least one carrier material (B).
9. (Currently Amended) The pigment preparation ~~as claimed in any of~~
~~claims 3 to 6 and 8 of claim 3~~, having a solids content of from 20 to 80% by
weight.
10. (Currently Amended) The pigment preparation ~~as claimed in any of~~
~~claims 1 to 9 of claim 1~~, comprising ~~at least one further~~ constituent (D)
selected from the group consisting of additives and dyes.
11. (Currently Amended) The pigment preparation ~~as claimed in~~ of claim 10,
wherein the additives are selected from the group consisting of crosslinking
agents, UV absorbers, light stabilizers, free-radical scavengers,
devolatilizers, slip additives, polymerization inhibitors, crosslinking
catalysts, thermolabile free-radical initiators, photoinitiators, thermally
curable reactive diluents, reactive diluents curable with actinic radiation,
adhesion promoters, leveling agents, film-forming auxiliaries, flame
retardants, corrosion inhibitors, free-flow aids, waxes, and flattening agents
and mixtures thereof.

12. (Currently Amended) The pigment preparation ~~as claimed in any of claims 1 to 11~~ of claim 1, wherein the dispersing apparatus is a kneading apparatus.

13. (Currently Amended) A process for producing a pigment preparation as ~~claimed in any of claims 1 to 12~~ of claim 1 by mixing together its constituents (A) and (B) and ~~also, where appropriate, optionally~~ (C) and/or (D), ~~which comprises~~ comprising

(1) in a first step in dispersing apparatus

- dispersing the pigment or pigments (A) or
- the pigment or pigments (A) and at least one constituent (D)
in the melt
- of the carrier material or carrier materials (B) or
- of the carrier material or carrier materials (B) and at least one constituent (D)

with a power input of from 0.1 to 1 kW/kg for from 0.5 to 5 hours, and then

(2) in a second step discharging the resulting mixture (A/B) or (A/B/D) from the dispersing apparatus and allowing it to cool and solidify.

14. (Original) The process as claimed in claim 13, wherein

(3) the solidified mixture (A/B) or (A/B/D) is pulverized.

15. (Currently Amended) The process ~~as claimed in claim 13 or 14~~ of claim 13, wherein

(4) the solidified mixture (A/B) or (A/B/D) is dispersed in at least one organic solvent (C).

Claims 16-22 (canceled)

23. (New) A coating comprising at least one of a pigmented powder coating or liquid coating material based on organic solvents comprising the pigment preparation of claim 1.
24. (New) A mixer system comprising the pigment preparation of claim 1, for producing or tinting at least one of powder coating material or solvent based coating materials.
25. (New) A mixer system according to claim 24 comprising
- (I) at least two adjustment modules each comprising a dispersion as set forth in claim 1 and
 - (II) at least one solids module comprising pigmented or unpigmented, dimensionally stable powders.
26. (New) A powder coating composition according to claim 23 wherein the oligomers and polymers (B) of the pigment preparation, are identical with the binders present in the powder coating.
27. (New) A powder coating composition according to claim 23, wherein the powders are polymer pellets or powder coating materials.
28. (New) A substrate coated with a powder coating according to claim 23, where said substrate is selected from the group consisting of
- interior and exteriors of transportation including at least one of aircraft, rail vehicles, watercraft, and automobiles,
 - components of transportation vehicles,
 - building interiors and exteriors,
 - doors, windows, furniture, hollow glassware,
 - pipelines,
 - coils, containers, mechanical, optical, and electrical components;

household appliances, boilers, radiators;
flanges, valves, wall-fitted wardrobes, bed frames, insulation boxes,
fence posts, garden furniture, traffic barriers, road signs, shopping
baskets, inserts for dishwashers, brake cylinders, laboratory equipment,
and chemical plants.